

Halar® 6514

chlorotrifluoroethylene polyethylene

Halar 6514 is a black, semi-crystalline melt processable fluorinated primer. It is designed to be applied directly to substrates by electrostatic or fluidized bed techniques. In particular Halar 6514 is recommended for use as a primer in protection and anti-corrosion applications.

Halar 6514 provides optimum and rapid bonding and can be used to maximize topcoat adhesion performance. It also exhibits both outstanding permeation and flame resistance, very good thermal properties and very good chemical resistance.

Main features of Halar 6514 include:

- Black color
- Optimum and rapid adhesion
- Outstanding permeation resistance
- Optimum flame resistance
- Very good thermal properties
- Very good chemical resistance

General

| | | | |
|-------------------|---|---|--------------------|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Europe • North America | • South America |
| Features | • Bondability • Flame Retardant • Good Adhesion | • Good Chemical Resistance • Good Corrosion Resistance • Good Thermal Stability | • Semi Crystalline |
| Uses | • Bonding | • Coating Applications | |
| Appearance | • Black | | |
| Forms | • Powder | | |
| Processing Method | • Coating | | |

Physical

| | Typical Value | Unit | Test Method |
|---|---------------|-------------------|---------------|
| Density | 1.65 to 1.71 | g/cm ³ | ASTM D3275 |
| Melt Mass-Flow Rate (MFR) (275°C/2.16 kg) | 9.0 to 15 | g/10 min | ASTM D3275 |
| Average Particle Size ¹ | 3.1 | mil | ASTM D1921-63 |

Thermal

| | Typical Value | Unit | Test Method |
|---------------------|---------------|------|-------------|
| Melting Temperature | 428 to 441 | °F | ASTM D3275 |

Additional Information

Processing

- Halar 6514 is intended as a primer material to apply directly to substrates. It can be processed using either conventional electrostatic powder coating or fluidized bed equipment.
- In the case of electrostatic coating the procedure involves substrate preparation, spray coating, baking and cooling. Several passes maybe required to obtain the desired Halar load and ensure pin-hole free coatings. Alternatively using fluidized bed equipment preheated items can be coated by dipping directly into the fluidized powder followed by baking. The dipping and baking operation can be repeated to achieve multiple coats and build up the desired coating thickness.
- Halar 6514 can be used neat and without any further formulation. For both techniques, substrate preparation, preheating, coating and baking parameters must all be well controlled to achieve defect free coated items and optimum adhesion.

Storage and Handling

- Halar melt processable fluoropolymer resins can be stored without shelf life issues when kept in a clean and dry area at ambient temperatures. Opened containers should be tightly resealed to prevent dust contamination.

Safety and Toxicology

- Before using Halar melt processable fluoropolymer resins consult the product Material Safety Data Sheet and follow all label directions an handling precautions.
- As with all fluoropolymer materials, handling and processing should only be carried out in well ventilated areas. Vapour extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapour or fumes.
- See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

- Halar 6514 is packaged in 25kg non returnable drums. Each drum has two bags liner made of polyethylene resin.

Notes

Typical properties: these are not to be construed as specifications.

¹ Method C

www.SolvaySpecialtyPolymers.com

Contact Solvay Specialty Polymers

Europe, Middle East and Africa SpecialtyPolymers.EMEA@solvay.com
Americas SpecialtyPolymers.Americas@solvay.com
Asia and Australia SpecialtyPolymers.Asia@solvay.com

For assistance with an emergency involving this product, such as spill, leak, fire or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590

International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300

+1.703.527.3887 (CHEMTREC)

Europe +44.208.762.8322 (CARECHEM)

China +86.10.5100.3039

All other Asian countries +65.633.44.177

For additional product information, technical assistance and Material Safety Data Sheets (MSDS), call:

USA + 1.800.621.4557 / +1.770.772.8760

Europe +49.211.5135.9000

Japan +81.3.5425.4300

China & Southeast Asia +86.21.5080.5080

Material Safety Data Sheets (MSDS) for products of Solvay Specialty Polymers are available upon request from your sales representative or by emailing us at specialtypolymers@solvay.com. Always consult the appropriate MSDS before using any of our products.

Solvay Specialty Polymers is comprised of the activities of the Solvay Advanced Polymers, Solvay Solexis and Solvay Padanaplast companies along with the Ixan® and Diofan® PVDC products lines. To our actual knowledge, the information contained herein is accurate as of the date of this document. However the companies that comprise Solvay Specialty Polymers and none of their affiliates make any warranty, express or implied, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for implantable medical devices; Solvay Specialty Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. All companies comprising Solvay Specialty Polymers reserve the right to make additions, deletions or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are property of the companies that comprise Solvay Specialty Polymers or their respective owners.
© 2012 Solvay Specialty Polymers. All rights reserved.

